THE FACTS ABOUT FILLINGS

Dental Materials Fact Sheet

What About the Safety of Fillings Materials?

Patient health and the safety of dental treatments are the primary goals of California's dental professionals and the Dental Board of California. The purpose of this fact sheet is to provide you with information concerning the risks and benefits of all the dental materials used in the restoration (filling) of teeth. The Dental Board of California is required by law* to make this dental materials fact sheet available to every licensed dentist in the state of California. Your dentist, in turn, must provide this fact sheet to every new patient and all patients of record only once before beginning any dental filling procedure. As the patient or parent/guardian, you are strongly encouraged to discuss with your dentist the facts presented concerning the filling materials being considered for your particular treatment. *Business and Professional Code 1648.10-1648.20

Allergic Reaction to Dental Materials

Components in dental fillings may have side effects or cause allergic reactions, just like other materials we may come in contact with in our daily lives. The risks of such reactions are very low for all types of filling materials. Such reactions can be caused by specific components of the filling material such as mercury, nickel, chromium, and/or beryllium alloys. Usually, an allergy will reveal itself as a skin rash and is easily reversed when the individual is not in contact with the material. There are no documented cases of allergic reactions to composite resin, glass ionomer, resin ionomer, or porcelain. However, there have been rare allergic responses reported with dental amalgam, porcelain fused to metal, gold alloys, and nickel or cobalt-chrome alloys. If you suffer form allergies, discuss these potential problems with your dentist before a filling material is chosen.

Toxicity of Dental Materials

Dental Amalgam

Mercury in its elemental form is on the State of California's Proposition 65 list of chemicals known to the state to cause reproductive toxicity. Mercury may harm the developing brain of a child or fetus. Dental amalgam is created by mixing elemental mercury (43-57%) and an alloy powder (46-57%) composed mainly of silver, tin, and copper. This has caused discussions about the risks of mercury in dental amalgam. Such mercury is emitted in minute amounts as vapor. Some concerns have been raised regarding possible toxicity. Scientific research continues on the safety of dental amalgam. According to The Centers for Disease Control and Prevention, there is scant evidence that the health of the vast majority of people with amalgams is compromised. The Food and Drug Administration (FDA) and other public health organizations have investigated the safety of amalgam used in dental fillings. The conclusions: no valid scientific evidence has shown that amalgams cause harm to patients with dental restorations, except in rare cases of allergy. The World Health Organization reached a similar conclusion stating, "Amalgam restorations are safe and cost effective." A diversity of opinions exists regarding the safety of dental amalgam. Questions have been raised about its safety in pregnant women, children, and diabetics. However scientific evidence and research literature in peer-reviewed journals suggest that otherwise healthy women, children, and diabetics are not at an increased risk from dental amalgams in their mouths. The FDA places no restrictions on the use of amalgam.

Some Composite Resins include Crystalline Silica, which is on the State of California's Proposition 65 list of chemicals known to the state to cause cancer. It is always a good idea to discuss any dental treatment thoroughly with your dentist.

Dental Amalgam Fillings - Dental amalgam is a self-hardening mixture of silver-tin-copper alloy powder and liquid mercury and is sometimes referred to as silver fillings because of its color. It is often used as a filling material and replacement for broken teeth

| Self-sealing; minimal-to-no snrinkage and resists leakage Resistance to further decay is high, but can be | Disadvantages Refer to "What About the Safety of Filling Materials" Gray colored, not tooth colored May darken as it corrodes; may stain teeth over time. Requires removal of some healthy teeth In larger amalgam fillings, the remaining tooth may weaken and fracture Because metal can conduct hot and cold temperatures, there may be a temporary sensitivity to hot and cold. Contact with other metals may cause occasional, minute electrical flow. |
|--|--|
|--|--|

Composite Resin Fillings - Composite fillings are a mixture of powdered glass and plastic resin, sometimes referred to as white, plastic, or tooth-colored fillings. It is used for fillings, inlays, veneers, partial and complete crowns, or to repair portions of broken teeth.

| | Advantages | | Disadvantages |
|---|--|---------|---|
| ٠ | Strong and durable | \succ | Refer to "What About the Safety of Filling Materi- |
| ٠ | Tooth colored | | als" |
| ٠ | Single visit for fillings | \succ | Moderate occurrence of tooth sensitivity; sensitive |
| ٠ | Resists breaking | | to dentist's method of application |
| ٠ | Maximum amount of tooth preserved | > | Costs more than dental amalgam |
| ٠ | Small risk of leakage if bonded only to enamel | > | Material shrinks when hardened and could lead to |
| ٠ | Does not corrode | | further decay and/or temperature sensitivity Requires more than one visit for inlays, veneers, |
| ٠ | Generally holds up well to the forces of biting | 1 | and crowns |
| | depending on product used | ≻ | May wear faster than dental enamel |
| ٠ | Resistance to further decay is moderate and easy to find | À | |
| ٠ | Frequency of repair or replacement is low to moderate | | |

Glass Ionomer Cement - Glass ionomer cement is a self hardening mixture of glass and organic acid. It is tooth-colored and varies in translucency. Glass ionomer is usually used for small fillings, cementing metal, and porcelain / metal crowns, liners, and temporary restorations.

Advantages

Disadvantages

- Reasonably good esthetics Cost is very similar to composite resin (which costs more than amalgam) May provide some help against decay because Limited use because it is not recommended for it releases fluoride biting surfaces in permanent teeth. Minimum amount of tooth needs to be re-As it ages, this material may become rough and moved and it bonds well to both the enamel could increase the accumulation of plaque and and the dentin beneath the enamel chance of periodontal disease Material has low incidence of producing tooth Does not wear well; tends to crack over time and sensitivity
- Usually completed in one dental visit
- can be dislodged

Resin-Ionomer Cement - Resin ionomer cement is a mixture of glass and resin polymer and organic acid that hardens with exposure to a blue light used in the dental office. It is tooth colored but more translucent that glass ionomer cement. It is most often used for small fillings, cementing metal and porcelain / metal crowns and liners.

Advantages Very good esthetics

- Way provide some help against decay because it releases fluoride
- Minimal amount of tooth needs to be removed and it bonds well to both the enamel and the dentin beneath the enamel
- Good for non-biting surfaces
- Maybe used for short-term primary teeth restorations
- May hold up better than glass ionomer but not as well as composite
- Good resistance to leakage
- Material has low incidence of producing tooth sensitivity
- Usually completed in one dental visit

Porcelain (Ceramic) - Porcelain is a glass-like material formed into fillings or crowns using models of the prepared teeth. The material is tooth colored and is used for inlays, veneers, crowns and fixed bridges.

Advantages

- Disadvantages Material is brittle and can break under biting
- Very little tooth needs to be removed for use as a veneer; more tooth needs to removed for a crown because it's strength is related to it's May n bulk
 Good resistance to further decay if restoration
- Good resistance to further decay if restoration fits well
- Is resistant to surface wear but can cause some wear on opposing teeth
- Resists leakage because it can be shaped for a very accurate fit
- The material does not cause tooth sensitivity

Nickel or Cobalt-Chrome Alloys - Nickel or cobalt-chrome alloys are mixtures of nickel and chromium. They are a dark silver metal color and are used for crowns, fixed bridges and partial denture frameworks.

Advantages

- Good resistance to further decay if the restoration fits well
 Excellent durability; does not fracture under
- stressDoes not corrode in the mouth
- Does not corrode in the mouth
 Minimal amount of tooth and a
- Minimal amount of tooth needs to be removed
 Resists leakage because it can be shaped for a very accurate fit

Porcelain Fused to Metal – This type of porcelain is a glass-like material that is "enameled" on top of metal shells. It is tooth-colored and is used for crowns and fixed bridges.

Advantages

Disadvantages

- Good resistance to further decay if the restoration fits well
 Very durable, due to metal substructure
 The material does not cause tooth sensitivity
 Resists leakage because it can be shaped for a
 More tooth needs to be removed (than for porcelain) for the metal substructure
 Higher cost because it requires at least two office visits
- very accurate fit

very accurate fit

Gold Alloy – Gold alloy is a gold-colored mixture of gold, copper, and other metals and is used mainly for crowns and fixed bridges and some partial denture frameworks.

Advantages Disadvantages Good resistance to further decay if the restoration fits well > Is not tooth colored; alloy is yellow Excellent durability; does not fracture under stress > Conducts heat and cold; may irritate sensitive teeth Does not corrode in the mouth > High cost; requires at least two office visits and laboratory services Minimal amount of tooth needs to be removed > Resists leakage because it can be shaped for a

The durability of any dental restoration is influenced by not only the material it is made from but also by the dentist's technique when placing the restoration. Other factors include the supporting materials used in the procedure and the patient's cooperation during the procedure. The length of time a restoration will last is dependent upon your dental hygiene, home care, diet and chewing habits.

Dental Board of California 1432 Howe Avenue • Sacramento, California 95825 www.dbc.ca.gov Published by California Department of Consumer Affairs 05/04

Disadvantages

- Cost is very similar to composite resin (which cost more than amalgam)
- Limited use because it is not recommended for biting surfaces in permanent teeth
- Wears faster than composite and amalgam

forces May not be recommended for molar teeth

- Higher cost because it requires at least two office visits and laboratory services
- xtures of nickel and chromium. They are a dark silve
 - **Disadvantages** Is not tooth colored; alloy is a dark silver color
- Conducts heat and cold; may irritate sensitive teeth
 Can be abrasive to opposing teeth
 High cost; requires at least two office visits and
 - rign cost; requires at least two office visits and laboratory services
 - \succ Slightly higher wear to opposing teeth